

Material Specification

Nomex



KE FIBERTEC

AIR THE WAY YOU WANT

MATERIAL: Nomex material is woven by KE Fibertec Væveri (weaving mill) using NM 60/2 yarns. The Nomex fibre is well-known for its flame resistant properties meaning that it will neither melt, drip nor combust in air. The Nomex material of KE Fibertec is woven in a twill weave using staple fibres to ensure largest possible textile surface and uniform air permeability.

CONSTRUCTION: Heatset, shrinkage- and permeability-stabilised material.

Type KE-Datasheet		NO130 33	NO290 16	NO370 17	NO460 18	NO700 19	Standard
Weight (%) -/+5	g/m²	298	250	230	220	210	EN-ISO 5077
Thickness (%) -/+10	mm	0.44	0.55	0.57	0.55	0.5	EN-ISO 12127:1997
Permeability	m³/m²/h 120 Pa Tolerance (%)	130	290	370	460	700	EN ISO 9237:1995
		-9/+9	-14/+14	-9/+9	-8/+8	-5/+5	
Tensile strength (%) -/+10	Warp / Weft N	1500 / 850	1550 / 1100	1550 / 1000	1600 / 950	1600 / 800	EN-ISO 13934-1
Resistance to tearing (%) -/+10	Warp / Weft N	170 / 170	120 / 110	120 / 120	140 / 100	150 / 140	EN-ISO 13937:2
*Filter class		N/A	N/A	N/A	N/A	N/A	EN 779:2012
**Shrinkage in wash	(%) 40°C	-	-	-	-	-	EN-ISO 5077
Melting point	°C	371	371	371	371	371	
Operating temperature	°C	100/-45	100/-45	100/-45	100/-45	100/-45	
Spontaneous ignition temp.	°C	-	-	-	-	-	
Water absorption	(%) at 90% RF	5	5	5	5	5	
Electrostatic resistance	Ohm	≤3 x 10 ⁸	≤3 x 10 ⁸	≤3 x 10 ⁸	≤3 x 10 ⁸	≤3 x 10 ⁸	DIN 54345-1
Clean room classification		N/A	N/A	N/A	N/A	N/A	ISO-14644-1
Fire resistance		B-S1-d0 N/A	B-S1-d0 N/A	B-S1-d0 N/A	B-S1-d0 N/A	B-S1-d0 N/A	EN-13501 UL 723/NFPA 90 A
Oeko-Tex®		Approved	Approved	Approved	Approved	Approved	Standard 100
Cradle to Cradle®		N/A	N/A	N/A	N/A	N/A	

*KE measurement **Washed and dried according to KE Fibertec instructions

This document and all information thereon is the property of KE Fibertec AS. It must not be copied, imparted to a third party or used for any other purpose without the written consent of KE Fibertec AS.

12/2024

KE Fibertec AS
Industrivej Vest 21
DK-6600 Vejen

T: +45 7536 4200
info@ke-fibertec.dk
www.ke-fibertec.com

