


# MULTIWEAVE®

## MATERIAL DATASHEET 44

KE-no.:	MW320		
Construction:	High Tenacity polyester fabric		
Final treatment:	Heat-set, shrinkage- and permeability-stabilized		
Weight	g/m <sup>2</sup> :	230	(%) - 5/+ 5
Thickness	mm:	0.40	(%) -10/+10
Tensile strength warp/weft	N/50 mm:	>2800 / >1300	(%) -10/+10
Resistance to tearing warp/weft	N:	200 / 160	(%) -10/+10
Permeability	m <sup>3</sup> /m <sup>2</sup> /h:	320 at 120 Pa	(%) -6/+15
Retention grade	:	F7 (*)	
Shrinkage in wash	%:	< 0.5 (**)	
Fire resistance	:	Flame retardant	
Melting point	°C:	254	
Spontaneous ignition temperature	°C:	508	
Water absorption (in standard climate)	%:	0.40	
Electrostatic resistance	Ohm/cm:	2 x 10 <sup>10</sup>	
Operating temperature max./min. (peak)	°C:	+60/-45 (peak: 80)	
Resistance to aging	:	Excellent	
Resistance to vibrations, motion	:	Excellent	
Resistance to solvents	:	Excellent	
Resistance to acids	:	Good	
Resistance to bases	:	Medium	
Resistance to oxidants, light, etc.	:	Excellent	



Quality grades: Excellent • Good • Medium • Less good • Not recommended

Comments: (\*) Recomm. KE-measurement • (\*\*) Washed and dried acc. to KE Fibertec instruction

*This document and all information thereon is the property of KE Fibertec AS. It must not be copied, imparted to a third party or used for any other purpose without the written consent of KE Fibertec AS.*

Data are subject to alterations.