


NOMEX

MATERIAL DATASHEET 18

KE-no.:	NO460		
Construction:	Nomex fabric		
Final treatment:	Heat-set		
Weight	g/m ² :	220	(%) -10/+10
Thickness	mm:	0.55	(%) -10/+10
Tensile strength warp/weft	N/50 mm:	1600 / 1100	(%) -10/+10
Resistance to tearing warp/weft	N:	140 / 100	(%) -10/+10
Permeability	m ³ /m ² /h:	460 at 120 Pa	(%) - 8/+ 8
Retention grade	:	F5 (*)	
Shrinkage in wash	%:	-	
Fire resistance	:	Flame retardant	
Melting point	°C:	371	
Spontaneous ignition temperature	°C:	-	
Water absorption (in standard climate)	%:	5	
Electrostatic resistance	Ohm/cm:	3 x 10 ⁸	
Operating temperature max./min. (peak)	°C:	+80/-40 (peak: 100)	
Resistance to aging	:	Excellent	
Resistance to vibrations, motion	:	Excellent	
Resistance to solvents	:	Excellent	
Resistance to acids	:	Not recommended	
Resistance to bases	:	Good	
Resistance to oxidants, light, etc.	:	Good	



Quality grades: Excellent • Good • Medium • Less good • Not recommended

Comments: (*) Recomm. KE-measurement • (**) Washed and dried acc. to KE Fibertec instruction

This document and all information thereon is the property of KE Fibertec AS. It must not be copied, imparted to a third party or used for any other purpose without the written consent of KE Fibertec AS.

Data are subject to alterations.