


NOMEX

MATERIAL DATASHEET 16

KE-no.:	N016		
Construction:	Nomex fabric		
Final treatment:	Heat-set		
Weight	oz/yd ² :	7.4	(%) -10/+10
Thickness	mil:	22	(%) -10/+10
Tensile strength warp/weft	lb _f /in:	183 / 148	(%) -10/+10
Resistance to tearing warp/weft	lb _f :	27 / 25	(%) -10/+10
Permeability	CFM/ft ² :	16 at 0.5 inWG	(%) -14/+14
Retention grade	:	F6 (*)	
Shrinkage in wash	%:	-	
Fire resistance	:	Flame retardant	
Melting point	°F:	700	
Spontaneous ignition temperature	°F:	-	
Water absorption (in standard climate)	%:	5.00	
Electrostatic resistance	Ohm/cm:	3 x 10 ⁸	
Operating temperature max./min. (peak)	°F:	+176/-40 (peak: 212)	
Resistance to aging	:	Excellent	
Resistance to vibrations, motion	:	Excellent	
Resistance to solvents	:	Excellent	
Resistance to acids	:	Not recommended	
Resistance to bases	:	Good	
Resistance to oxidants, light, etc.	:	Good	



Quality grades: Excellent • Good • Medium • Less good • Not recommended

Comments: (*) Recomm. KE-measurement • (**) Washed and dried acc. to KE Fibertec instruction

This document and all information thereon is the property of KE Fibertec AS. It must not be copied, imparted to a third party or used for any other purpose without the written consent of KE Fibertec AS.

Data are subject to alterations.