


# NOMEX

## MATERIAL DATASHEET 33

KE-no.:	N08		
Construction:	Nomex fabric		
Final treatment:	Heat-set		
Weight	oz/yd <sup>2</sup> :	8.8	(%) -5/+5
Thickness	mil:	17	(%) -10/+10
Tensile strength warp/weft	lb <sub>f</sub> /in:	148 / 160	(%) -10/+10
Resistance to tearing warp/weft	lb <sub>f</sub> :	38 / 38	(%) -10/+10
Permeability	CFM/ft <sup>2</sup> :	8 at 0.5 inWG	(%) -15 / +15
Retention grade	:	F5 (*)	
Shrinkage in wash	%:	-	
Fire resistance	:	Flame retardant	
Melting point	°F:	700	
Spontaneous ignition temperature	°F:	-	
Water absorption (in standard climate)	%:	5.00	
Electrostatic resistance	Ohm/cm:	3 x 10 <sup>8</sup>	
Operating temperature max./min. (peak)	°F:	+176/-40 (peak: 212)	
Resistance to aging	:	Excellent	
Resistance to vibrations, motion	:	Excellent	
Resistance to solvents	:	Excellent	
Resistance to acids	:	Not recommended	
Resistance to bases	:	Good	
Resistance to oxidants, light, etc.	:	Good	



Quality grades: Excellent • Good • Medium • Less good • Not recommended

Comments: (\*) Recomm. KE-measurement • (\*\*) Washed and dried acc. to KE Fibertec instruction

*This document and all information thereon is the property of KE Fibertec AS. It must not be copied, imparted to a third party or used for any other purpose without the written consent of KE Fibertec AS.*

Data are subject to alterations.